

Material Properties

Bar Manifolds and Accessories are offered in the following standard materials;
6061-T6 Aluminum, 65-45-12 Continuous Cast Ductile Iron and C12L14 free machining steel.

Other materials such as Stainless Steel, Mild Steel, Brass, and Plastic are available upon request.
Below, are the properties of the standard materials:

For its aluminum bodies, a 6000 series aluminum alloy that offers high strength characteristics and good corrosion resistance in the finished product is used. The mechanical properties of grade 6061-T6 aluminum are:

ALUMINUM PROPERTIES PROPERTIES	ASTM B-221 ** Grade 6061-T6
Tensile Strength	45,000 PSI
Yield Strength	40,000 PSI
Elongation, %	12%
Brinell Hardness Range	95
ASTM Specification	B-221

**Above material is rated at 3000 psi max, depending on duty cycle and design parameters.

We use a ductile iron that offers high tensile strength and good ductility for its iron bodies. All ductile iron bodies use iron produced by the continuous cast method which provides a body that possesses a dense, homogeneous structure with minimal inclusions for high pressure integrity. The mechanical properties of grade 65-45-12 ductile iron are:

DUCTILE IRON PROPERTIES	ASTM A-536 ** Grade 65-45-12
Tensile Strength	65,000 PSI
Yield Strength	45,000 PSI
Elongation, %	12%
Brinell Hardness Range	131/220
ASTM Specification	A-536

**Above material is rated at 5000 psi max, depending on duty cycle and design parameters.

Where applicable, a free machining grade of steel is used on select bodies. The mechanical properties of this material are equal to or greater than ductile iron. The mechanical properties of grade C12L14 are:

FREE MACHINING STEEL PROPERTIES	ASTM A-108 ** Grade C12L14
Tensile Strength	78,000 PSI
Yield Strength	70,000 PSI
Elongation, %	15%
Brinell Hardness Range	163
ASTM Specification	A-108

**Above material is rated at 5000 psi max, depending on duty cycle and design parameters.

THIS DATA IS FOR REFERENCE ONLY. CONSULT THE APPROPRIATE STANDARDS FOR CRITICAL DIMENSIONS AND RATINGS.

WE RESERVE THE RIGHT TO DISCONTINUE MODELS, OR CHANGE SPECIFICATIONS WITHOUT NOTICE OR INCURRING OBLIGATION

Lynch Products Can Be Modified to Suit Your Application

Phone: 1 (888) 626-4365 or + 1 (905) 363-2400 Fax: 1 (800) 263-5807 www.lynch.ca sales@lynch.ca